

Description + Application:

Myaktiv 75 is a rubber powder from recycled truck tyres with the addition of an adhesion improver, used for rubber-modified asphalts.

Grain composition:

0,1 - 0,6 mm

Physical characteristics:

Characteristic		Test method
Density at 15°C	1,10 - 1,20 g/cm ³	DIN EN 12185
Bulk density	0,5 - 0,6 g/cm ³	DIN EN 12185
Flash point	> 220 °C	DIN ISO 2592

Material composition:

Content of rubber powder	> 80 M.- %
Content of adhesion improver	> 10 M.- %
Content of activating additive	< 10 M.- %

Packaging unit:

- 20 kg PE bags
- Big Bag 500 kg or 1.000 kg

Dispatch:

Self-Collection or free house delivery

Storage information:

dry, not too warm, no direct sunlight

The information is based on our current experience in manufacturing and application. The values and average values contained therein serve as non-binding advice and information. It is the responsibility of the user to check the suitability for his intended use.